LEACH GARNER
A Berkshire Hathaway Company

14K#352

Precious Metals	
Gold:	58.33%
Silver:	8.0%
Palladium:	-

Properties	
Density:	136.8 dwt/in^3 (13.0 g/cm^3)
Color:	Yellow
Melting Temperature – Liquidus:	1605F (875°C)
Casting Temperature:**	1735F (945°C)
Flask temperature:**	1100F-1200F

** These are typical values and may be altered depending on the equipment and technique used in a particular casting facility set up.